


<b>Membrane Element</b>		<b>ESPA - 4021</b>
<b>Performance</b>	Permeate Flow:	1,000 gpd (3.8 m <sup>3</sup> /d)
	Salt Rejection:	99.4 % (98.0% minimum)
<b>Type</b>	Configuration:	Spiral Wound
	Membrane Polymer:	Composite Polyamide
	Membrane Active Area:	28.6 ft <sup>2</sup>
<b>Application Data*</b>	Maximum Applied Pressure:	300 psig (2.1 MPa)
	Maximum Chlorine Concentration:	< 0.1 PPM
	Maximum Operating Temperature:	113° F (45°C)
	pH Range; Continuous (Cleaning):	3.0 –10.0*
	Maximum Feedwater Turbidity:	1.0 NTU
	Maximum Feedwater SDI (15 mins):	4.0
	Maximum Feed Flow:	12 GPM (45.4 l/m)
	Minimum Ratio of Concentrate to Permeate Flow for any element:	5:1
	Maximum Pressure Drop for Each Element:	10 psi

\* The limitations shown here are for general use. For specific projects, operating at more conservative values may ensure the best performance and longest life of the membrane. See Hydranautics Technical Bulletins for more detail on operation limits, cleaning pH, and cleaning temperatures.

### Test Conditions

Elements are wet tested for quality assurance using the following conditions:

1500 PPM NaCl solution  
 150 psi (1.03 MPa) Applied Pressure  
 77 °F (25 °C) Operating Temperature  
 10% Permeate Recovery  
 6.5 – 7.0 pH Range  
 (Data taken after 30 minutes of operation)



A, inches (mm)	B, inches (mm)	C, inches (mm)	Weight, lbs. (Kg)
21.0 (533.4)	3.95 (100.3)	0.75 (19.1)	4 (1.8)

**Core tube extension = 1.10" (27.9 mm)**

**Notice:** Minimum permeate flow for individual elements is 15 percent below listed flow. All membrane elements are supplied with a brine seal and o-rings. Most elements are packaged dry, sealed in polyethylene bags, and shipped in a cardboard box. Some elements are sealed in polyethylene bags containing less than 1.0% sodium meta-bisulfite solution and shipped in a cardboard box.

Hydranautics believes the information and data contained herein to be accurate and useful. The information and data are offered in good faith, but without guarantee, as conditions and methods of use of our products are beyond our control. Hydranautics assumes no liability for results obtained or damages incurred through the application of the presented information and data. It is the user's responsibility to determine the appropriateness of Hydranautics products for the user's specific end uses.

10/28/10